

VOC Pro Filler U7530

Standox VOC Pro Filler U7530 is a highly effective 2K filler for fast and economical refinish work. It is available in black, mid-grey and white.



- Efficient sanding filler that can be mixed with all Standox VOC and HS hardeners.
- Dries well and quickly at ambient air temperatures particularly in combination with the VOC Pro Filler Accelerator U7535.
- Can be sanded after 30 minutes drying at ambient temperatures of 20 °C when used with VOC Pro Filler Accelerator U7535.
- Helps to reduce energy consumption when preparing vehicles.
- VOC compliant.

P – Productive Line. Products delivering high-performance durable results with speed and precision. Engineered to minimize energy use, material waste, and elevate shop productivity.




The Art of Refinishing.

VOC Pro Filler U7530

Product preparation - application STANDARD SANDING VOC



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Steel, galvanised steel and soft aluminium sanded and cleaned and coated with 1K Acid Primer or Epoxy Primer. In addition, for small sand through areas, pre-treatment wipes can be used.
Old or original paintwork well sanded and cleaned.
OEM Primer (e-coat), sanded and cleaned.
Surfaces pretreated with 2K polyester products and then finely sanded and cleaned.
Glass fibre polyester substrates, free of release agents, sanded and cleaned.



Filler		Hardener		Thinner	
Volume	Weight	Volume	Weight	Volume	Weight
7	100	1	11	25 - 30 %	17 - 20
U7530		VOC 10-20 VOC 20-25 VOC 25-30 VOC 30-40		VOC T 15-30 VOC T 30-40	



Potlife at 20°C: 45 min - 1 hr



	Spray nozzle	Spray pressure	
Compliant	1.6 - 1.8	1.5 - 2 bar	inlet pressure
HVLP	1.6 - 1.8	0.7 bar	atomisation pressure

see manufacturer's instructions



2 - 3 coats intermediate and final flash-off: 5 min - 10 min



	VOC10-20/VOC20-25/VOC25-30/VOC30-40
20 °C	1 hr 30 min
60 - 65 °C	20 min - 30 min



Guideline for short wave IR equipment
Half power: 10 min



P500



2K Topcoat
Basecoat + Clearcoat

VOC compliant


2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

VOC Pro Filler U7530

Product preparation - application STANDARD SANDING HS



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Steel, galvanised steel and soft aluminium sanded and cleaned and coated with 1K Acid Primer or Epoxy Primer. In addition, for small sand through areas, pre-treatment wipes can be used.
Old or original paintwork well sanded and cleaned.
OEM Primer (e-coat), sanded and cleaned.
Surfaces pretreated with 2K polyester products and then finely sanded and cleaned.
Glass fibre polyester substrates, free of release agents, sanded and cleaned.



Filler		Hardener		Thinner	
Volume	Weight	Volume	Weight	Volume	Weight
5	100	1	14	20 %	14
U7530		HS 5-15 HS 15-25 HS 20-30 HS 25-40		2K 10-20 2K 15-25 2K 20-25 2K 25-35 2K 35-40 VOC T 15-30 VOC T 30-40	



Potlife at 20°C: 45 min - 1 hr



	Spray nozzle	Spray pressure	
Compliant	1.6 - 1.8	1.5 - 2 bar	inlet pressure
HVLP	1.6 - 1.8	0.7 bar	atomisation pressure

see manufacturer's instructions



2 - 3 coats intermediate and final flash-off: 5 min - 10 min



	HS5-15/HS15-25/HS20-30/HS30-40
20 °C	1 hr 30 min
60 - 65 °C	20 min - 30 min



Guideline for short wave IR equipment
Half power: 10 min



P500



2K Topcoat
Basecoat + Clearcoat

VOC compliant


2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

VOC Pro Filler U7530

Product preparation - application STANDARD SANDING MS



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Steel, galvanised steel and soft aluminium sanded and cleaned and coated with 1K Acid Primer or Epoxy Primer. In addition, for small sand through areas, pre-treatment wipes can be used.
Old or original paintwork well sanded and cleaned.
OEM Primer (e-coat), sanded and cleaned.
Surfaces pretreated with 2K polyester products and then finely sanded and cleaned.
Glass fibre polyester substrates, free of release agents, sanded and cleaned.



Filler		Hardener		Thinner	
Volume	Weight	Volume	Weight	Volume	Weight
4	100	1	17	15 - 20 %	12 - 16
U7530		MS 25-40		2K 10-20	
		MS 5-15		2K 15-25	
		MS X 15-30		2K 20-25	
		MS X 5-25		2K 25-35	
				2K 35-40	



Potlife at 20°C: 45 min - 1 hr



	Spray nozzle	Spray pressure	
Compliant	1.6 - 1.8	1.5 - 2 bar	inlet pressure
HVLP	1.6 - 1.8	0.7 bar	atomisation pressure

see manufacturer's instructions



2 - 3 coats intermediate and final flash-off: 5 min - 10 min



	MS5-15/MS25-40/MSX5-25/MSX15-30
20 °C	1 hr 30 min
60 - 65 °C	20 min - 30 min



Guideline for short wave IR equipment
Half power: 10 min



P500



2K Topcoat
Basecoat + Clearcoat

VOC compliant


This product mix is not VOC compliant.

VOC Pro Filler U7530

Product preparation - application STANDARD ACCELERATED VOC



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Steel, galvanised steel and soft aluminium sanded and cleaned and coated with 1K Acid Primer or Epoxy Primer. In addition, for small sand through areas, pre-treatment wipes can be used. Old or original paintwork well sanded and cleaned.

OEM Primer (e-coat), sanded and cleaned.

Surfaces pretreated with 2K polyester products and then finely sanded and cleaned.

Glass fibre polyester substrates, free of release agents, sanded and cleaned.



Filler		Hardener		Thinner	
Volume	Weight	Volume	Weight	Volume	Weight
5	100	1	15	35 %	26
U7530		VOC 10-20		U7535	




Potlife at 20°C: 20 min - 30 min



	Spray nozzle	Spray pressure	
Compliant	1.6 - 1.8	1.5 - 2 bar	inlet pressure
HVLP	1.6 - 1.8	0.7 bar	atomisation pressure

see manufacturer's instructions



2 - 3 coats

intermediate flash-off not needed



	U7535
20 °C	30 min



P500



2K Topcoat
Basecoat + Clearcoat

VOC compliant


2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

VOC Pro Filler U7530

Product preparation - application STANDARD ACCELERATED HS



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Steel, galvanised steel and soft aluminium sanded and cleaned and coated with 1K Acid Primer or Epoxy Primer. In addition, for small sand through areas, pre-treatment wipes can be used.
Old or original paintwork well sanded and cleaned.
OEM Primer (e-coat), sanded and cleaned.
Surfaces pretreated with 2K polyester products and then finely sanded and cleaned.
Glass fibre polyester substrates, free of release agents, sanded and cleaned.



Filler		Hardener		Thinner	
Volume	Weight	Volume	Weight	Volume	Weight
4	100	1	18	25 %	20
U7530		HS 15-25		U7535	




Potlife at 20°C: 20 min - 30 min



	Spray nozzle	Spray pressure	
Compliant	1.6 - 1.8	1.5 - 2 bar	inlet pressure
HVLP	1.6 - 1.8	0.7 bar	atomisation pressure

see manufacturer's instructions



2 - 3 coats intermediate flash-off not needed



	U7535
20 °C	30 min



P500



2K Topcoat
Basecoat + Clearcoat

VOC compliant

2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

VOC Pro Filler U7530

Products


VOC Pro Filler U7530

Standox Hardener HS 15-25
Standox Hardener HS 20-30
Standox Hardener HS 25-40
Standox Hardener HS 5-15
Standox Hardener MS 25-40
Standox Hardener MS 5-15
Standox Hardener MS X 15-30
Standox Hardener MS X 5-25
Standox Hardener VOC 10-20
Standox Hardener VOC 20-25
Standox Hardener VOC 25-30
Standox Hardener VOC 30-40

Standox Thinner 2K 10-20
Standox Thinner 2K 15-25
Standox Thinner 2K 20-25
Standox Thinner 2K 25-35
Standox Thinner 2K 35-40
Standox Thinner VOC 15-30
Standox Thinner VOC 30-40
VOC Pro Filler Accelerator U7535

VOC Pro Filler U7530

Product mix




Mixing ratios with special agents are available in the productmix table on Standwin IQ and in the specific TDS.


The choice of hardener and Thinner should be made according to application temperature and size of repair.

VOC 10-20	Accelerated fast hardener suitable for Micro Repair, spot and panel repairs. Recommended for cooler application conditions e.g. 10-20°C.
VOC 20-25	Medium hardener suitable for panel and multi panel repairs. Recommended for application temperature of 20-25°C.
VOC 25-30	Medium-slow hardener suitable for medium to large size repairs. Recommended also for warm conditions e.g. 25-30°C.
VOC 30-40	Non-accelerated slow hardener suitable for medium to large size repairs. Recommended for use in hot climates e.g. 30-40°C.
HS 5-15	Accelerated fast hardener suitable for Micro and Spot repairs. Recommended for cooler application conditions. Suitable for Stadox Fillers for air drying at lower temperatures.
HS 15-25	Medium hardener suitable for panel and multi panel repairs. Recommended for application temperature of 15-25°C.
HS 20-30	Medium-slow hardener suitable for medium to large size repairs. Recommended also for warm conditions e.g. 20-30°C.
HS 25-40	Non-accelerated slow hardener suitable for medium to large size repairs. Recommended for use in hot climates e.g. 25-40°C.
MS 5-15	Accelerated fast hardener suitable for Micro and Spot repairs. Recommended for cooler application conditions. Suitable for Stadox Fillers for air drying at lower temperatures.
MS X 5-25	Fast hardener suitable for Micro Repair, Spot and panel repairs. Recommended for application temperature up to 25°C.
MS X 15-30	Medium hardener suitable for panel and multi panel repairs. Recommended also for warm conditions up to 30°C.
MS 25-40	Non-accelerated slow hardener suitable for medium to large size repairs. Recommended for use in hot climates e.g. 25-40°C.
2K 10-20	Accelerated fast thinner suitable for Micro Repair, spot and panel repairs. Recommended for cooler application conditions e.g. 10-20°C.
2K 15-25	Fast thinner suitable for Micro Repair, Spot and panel repairs. Recommended for temperature of 15-25°C.
2K 20-25	Medium thinner suitable for panel and multi panel repairs. Recommended for application temperature of 20-25°C.
2K 25-35	Medium-slow thinner suitable for medium to large size repairs. Recommended also for warm conditions e.g. 25-35°C.
2K 35-40	Slow thinner suitable for medium to large size repairs. Recommended for use in hot climates e.g. 35-40°C.
VOC T 15-30	Medium thinner suitable for panel, multi panel and large size repairs. Recommended for application temperature e.g. 15-30°C.
VOC T 30-40	Slow thinner for medium to large size repairs. Recommended for use in hot climates e.g. 30-40°C.
U7535	VOC Pro Filler Accelerator U7535 can be used in VOC Pro Filler U7530 only. In combination with selected VOC or HS Hardeners it will mainly expedite the air dry performance of VOC Pro Filler U7530. Potlife will be reduced.

VOC Pro Filler U7530



ISO 5: 25 - 30 s at 20°C
DIN 4: 22 - 25 s at 20°C



70 - 200 µm

Theoretical coverage

380 - 400 m²/l at 1 micron dry film thickness

Due to different hardener characteristics and different mixing ratios of the ready-to-use mixture in some TDS versions, the theoretical coverage calculation may vary.

Note: The practical material consumption depends on several factors, e.g. geometry of the object, surface formation, application method, spray gun setting, inlet pressure, etc.



Clean after use with a suitable solventbased guncleaner.

Remarks

- Material has to be at room temperature (18-25°C) before use.
- Surplus ready for use material should not be returned to original can.
- When isolating certain spots - even on problem substrates - the best results are achieved with a medium film thickness of 80-120µm in 2 coats, after either air drying overnight or force drying/IR drying. With problem substrates, careful pretreatment is necessary and the Filler must be applied to the entire area.
- Allow additional time for preheating up to panel temperature.
- The use of 2K Acid Primer underneath the surfacer is allowed, when the surfacer is intended to be forced dried or dried overnight.
- Mix thoroughly by hand before placing the can on mixing machine.
- In countries without VOC legislation Standox Basecoat/Standocryl 2K Topcoat/Standocryl 2K Topcoat NEW can be used as well.
- Force drying of Standox VOC Pro Filler U7530 with U7535 is possible with short wave I.R. for 5 minutes at half power, or 5 minutes at 60°C-65°C oven bake.
- In the Standard Sanding VOC setting the use of the VOC X Hardeners is also allowed.
- 15% of Standox Plasticiser 5660 can be added to the Filler before adding hardener, but mixing ration will change.
Mixed with Standox Hardeners VOC - 4:1 + 20% Standox Thinner VOC
Mixed with Standox Hardeners HS - 3:1 + 20% Standox Thinner VOC/2K
Mixed with Standox Hardeners MS - 2:1 + 20% Standox Thinner 2K

VOC Pro Filler U7530

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Standox product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Standox product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

